

EUROBOND Vitralit 4730

Product Description

Vitralit® adhesives are one-component, solvent-free radiation-curing adhesives. The advantages are very short curing times, good adhesion to a variety of substrates, and easy handling. Vitralit® products are used in electronics, medical applications, optics and for fixing parts in general.

Vitralit® 4730 is a UV and light-curing adhesive with very good adhesion to metals, glass, ceramics and many plastics.

Vitralit® 4730 is distinguished in the combination PMMA / glass. The cured product is optically clear and free of yellowing. The surface is dry. After curing, the adhesive provides excellent flexibility with sufficiently good adhesion.

Curing Properties

UV-A	VIS	Thermal curing	Activator curing
ü	ü	-	-

ü suitable - not suitable

The product cures within seconds with radiation in the UV-A - (320 nm - 390 nm) and visible range (405 nm). For rapid and high quality crosslinking we are UK distributors of UV devices manufactured by Dr. Hoenle AG, which complement our adhesive technology.

UV-curing (Hoenle Discharge lamp, 320-450nm)		
Intensity [mW/cm ²]	Layer thickness [mm]	Time [sec]
60	0,05	2
VIS-curing (Hoenle LED Spot 100, 405nm)		
Intensity [mW/cm ²]	Layer thickness [mm]	Time [sec]
100	0,05	10

To obtain full cure at least one substrate must be transparent to the recommended wavelength. The curing speed will depend on the intensity of light, light source, the exposure time, and the light transmittance of the substrate. Increased mechanical properties are achieved after 12 hours.

Technical Data

Resin acrylate Appearance transparent

Uncured material

Viscosity [mPas] [cP] (Brookfield LVT, 25°C, Sp 2, 60rpm)	70 - 150
PE-Norm 001	
Flash point [°C] PE-Norm 050	>93
Refractive index [nD20] PE-Norm 018	1,471

Contact Details

TECHSiL Limited
Unit 34, Bidavon Industrial Estate, Waterloo Road, Bidford on Avon, Warwickshire, B50 4JN
+44(0)1789 773232 | sales@techsil.co.uk | www.eurobond-adhesives.co.uk

Cured material

Hardness shore D PE-Norm 006	20 - 40
Temperature resistance [°C]	-40 - 120
Water absorption [mass %] PE-Norm 016	<4
Glass transition temperature DSC [°C] PE-Norm 009	20 - 30

Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	at room temperature max. 25°C	at room temperature max. 25°C	at delivery min. 6 months max. 12 months
Other packages			

*Store in original, unopened containers! Instructions for Use

Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IPA®. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pre-treated in order to achieve sufficient adhesion.

Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

After application, bonding of the parts should be done quickly. Vitralit® adhesives cure slowly in daylight. Therefore, we recommend to expose the material to as little light as possible and the use of opaque hose lines and dispensing needles.

For safety information refer to our safety data sheet.

DISCLAIMER

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process. Such information is, to the best of the company's knowledge and belief, accurate and reliable as of the date indicated. However, no warranty guarantee or representation is made to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability of such information for their particular use.

Contact Details

TECHSiL Limited
Unit 34, Bidavon Industrial Estate, Waterloo Road, Bidford on Avon, Warwickshire, B50 4JN
+44(0)1789 773232 | sales@techsil.co.uk | www.eurobond-adhesives.co.uk