

# LOCTITE<sup>®</sup> SF 7070<sup>™</sup>

Known as LOCTITE<sup>®</sup> 7070<sup>™</sup>  
December 2013

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> SF 7070<sup>™</sup> provides the following product characteristics:

<b>Technology</b>	Solvent cleaner
<b>Chemical Type</b>	Hydrocarbon / Monoterpene blend
<b>Appearance</b>	Colorless transparent liquid <sup>LMS</sup>
<b>Viscosity</b>	Very low
<b>Cure</b>	Not applicable
<b>Application</b>	Surface cleaner

LOCTITE<sup>®</sup> SF 7070<sup>™</sup> is a non-aqueous, hydrocarbon based, non-CFC solvent designed for cleaning and degreasing of surfaces to be bonded with LOCTITE<sup>®</sup> adhesives. The product is used as a final pre-assembly cleaning treatment to remove most greases, oils, lubrication fluids, metal cuttings and fines from surfaces to be bonded. It is designed to be used as a spray or in immersion cleaning processes at room temperature or heated.

## NSF International

**Registered to NSF Category K1** for use as a cleaner and degreaser in non food processing areas which are used to remove oil, wax, resinous materials, or other substances not removable by using acidic or alkaline cleaning agents. **Note:** This is a regional approval. Please contact your local Technical Service Center for more information and clarification.

## TYPICAL PROPERTIES

Specific Gravity @ 25 °C	0.75
Infrared Spectrum	As standard <sup>LMS</sup>
Viscosity @ 20°C, mPa·s (cP)	1 to 2
Drying Time @ 20 °C, minutes	5 to 20
Kauri-Butanol Value (KB)	31
Flash Point - See SDS	

## TYPICAL PERFORMANCE

LOCTITE<sup>®</sup> SF 7070<sup>™</sup> has no effect on the speed of cure or final strength of LOCTITE<sup>®</sup> adhesives other than providing a clean surface for good adhesion and adhesive cure. Unclean or partially cleaned surfaces can affect adhesive performance.

## Handling precautions

Cleaner must be handled in a manner applicable to highly flammable materials and in compliance with relevant local regulations.

Special care must be taken to avoid contact of the product or its vapour with naked flame or any electrical equipment that is not flame proofed.

The solvent can affect certain plastics or coatings. It is recommended to check all surfaces for compatibility before use.

LOCTITE<sup>®</sup> SF 7070<sup>™</sup> is compatible with metals, many plastics and elastomers.

The following table shows the effect of LOCTITE<sup>®</sup> SF 7070<sup>™</sup> on various plastics and elastomers. Since compatibility is affected by material variation, it is recommended to check parts and cleaning equipment gaskets, seals and O-rings under end use conditions before adopting use of LOCTITE<sup>®</sup> SF 7070<sup>™</sup>.

## LOCTITE<sup>®</sup> SF 7070<sup>™</sup> Compatibility with Plastics

Tested per ASTM D543

(All specimens weighed 30 minutes after removing from solvent)

Plastics	30 minutes @ 22 °C:	
	% Wt chg	Appearance
ABS	+0.05	No change
Acrylic	+0.11	No change
Polyacetal	+0.02	No change
G-10 Epoxy	+0.01	No change
Nylon 101	+0.14	No change
Nylon 66	+0.04	No change
Polycarbonate	+0.07	No change
Phenolic	+0.21	No change
Polyethylene (HD)	+0.05	No change
Polyethylene (LD)	+0.11	No change
Polypropylene	+0.06	No change
Polystyrene (High Impact)	+0.13	No change
Polystyrene	+0.13	No change
Polysulfone	+0.05	No change
PVC	+0.03	No change
Polytetrafluoroethylene	+0.02	No change
Polyetherimide	+0.09	No change
Polybutyleneterephthalate	+0.05	No change

Plastics	30 minutes @ 38 °C:	
	% Wt chg	Appearance
ABS	0	No change
Acrylic	+0.04	No change
Polyacetal	+0.01	No change
G-10 Epoxy	+0.01	No change
Nylon 101	+0.05	No change
Nylon 66	+0.02	No change
Polycarbonate	+0.03	No change
Phenolic	0.13	No change
Polyethylene (HD)	+0.1	No change
Polyethylene (LD)	0.39	No change
Polypropylene	+0.1	No change
Polystyrene (High Impact)	+0.28	No change
Polystyrene	+0.03	No change
Polysulfone	+0.03	No change
PVC	+0.03	No change
Polytetrafluoroethylene	+0.01	No change
Polyetherimide	+2.7	No change
Polybutyleneterephthalate	+0.04	No change

### LOCTITE® SF 7070™ Compatibility with Elastomers

Tested per ASTM D543

(All specimens weighed 30 minutes after removing from solvent)

Plastics	30 minutes @ 22 °C:	
	% Wt chg	Appearance
Buna-N	+0.9	Slight swelling
Buna-S	+0.48	Slight swelling
Butyl	+5.33	Swelling
EPDM	+5.23	Swelling
Neoprene	+1.08	Slight swelling
Polyurethane	+0.07	Slight swelling
Silicone	+10.8	Swelling
Fluoroelastomer	+1.08	Slight swelling

Plastics	30 minutes @ 38 °C:	
	% Wt chg	Appearance
Buna-N	+2.5	Swelling
Buna-S	+1.1	Slight swelling
Butyl	+8.2	Swelling
EPDM	+12.0	Swelling
Neoprene	+2.3	Swelling
Polyurethane	+0.07	Slight swelling
Silicone	+13.8	Swelling
Fluoroelastomer	0	Slight swelling

### GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected with a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

#### Directions for use:

1. Treat surfaces to be cleaned by spraying or wiping surfaces with a solvent soaked paper towel.
2. Wipe surfaces when still wet with a clean cloth to remove all heavy contamination. If necessary, spray surfaces again to allow run-off of product.
3. Repeat cleaning process if necessary.
4. Allow LOCTITE® SF 7070™ to fully evaporate from parts prior to bonding to avoid solvent entrapment within the bond joint.
5. Apply the Loctite® adhesive immediately after drying and assemble bond.

### Loctite Material Specification<sup>LMS</sup>

LMS dated March 23, 2005. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

#### Storage

The product is classified as flammable and must be stored in an appropriate manner in compliance with relevant regulations. Do not store near oxidizing agents or combustible materials. Store product in the unopened container in a dry location. Storage information may also be indicated on the product container labelling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

#### Conversions

(°C x 1.8) + 32 = °F  
 kV/mm x 25.4 = V/mil  
 mm / 25.4 = inches  
 µm / 25.4 = mil  
 N x 0.225 = lb  
 N/mm x 5.71 = lb/in  
 N/mm<sup>2</sup> x 145 = psi  
 MPa x 145 = psi  
 N·m x 8.851 = lb·in  
 N·m x 0.738 = lb·ft  
 N·mm x 0.142 = oz·in  
 mPa·s = cP

#### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others

over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

## Reference 1.2